

Anomalous flux-flow dynamics in layered type-II superconductors at low temperatures

M. V. Feigel'man and M. A. Skvortsov

L. D. Landau Institute for Theoretical Physics, Moscow 117940, RUSSIA

Low-temperature dissipation due to vortex motion in strongly anisotropic type-II superconductors with a moderate disorder ($\Delta^2/E_F \ll \hbar/\tau \ll \Delta$) is shown to be determined by the Zener-type transitions between the localized electronic states in the vortex core. Statistics of these levels is described by the random matrix ensemble of the class C defined recently by Atland and Zirnbauer [17], so the vortex motion leads naturally to the new example of a parametric statistics of energy levels. The flux-flow conductivity σ_{xx} is a bit lower than the quasiclassical one [4] and *grows* slowly with the increase of the electric field.

It is generally accepted that the flux-flow longitudinal (σ_{xx}) and Hall (σ_{xy}) conductivities in the mixed state of type-II superconductors are given, respectively, by the Bardeen-Steven (BS) [1] and Nozieres-Vinen [2] relations

$$\sigma_{xx} \approx \sigma_n \frac{H_{c2}}{B}; \quad \sigma_{xy} \approx (\omega_0 \tau) \sigma_{xx}, \quad (1)$$

where σ_n is the normal-state conductivity, τ is the elastic lifetime with respect to impurity scattering, and $\hbar\omega_0 \approx \Delta^2/E_F \ll \Delta$ (it is supposed in (1) that $\omega_0 \tau \ll 1$). The meaning of this relation is very simple: it reflects the fact that the core region of a vortex (of the area $\sim \xi^2$) may be considered (with respect to its electronic properties) just as a normal metal. This idea is based on the existence of localized electronic levels within the core [3], with energies constituting an equidistant set $E_\mu = \mu \hbar \omega_0$, where $\mu = i + 1/2$ and i is integer. A microscopic theory of flux-flow conductivities, which explicitly takes into account an existence of this level structure was developed long ago [4] (cf. also [5], [6], [7]). This theory is based on the quasiclassical nonequilibrium diagram technique (see e.g. [8]); its predictions for ρ_{xx} and ρ_{xy} basically coincide with the above simple picture as far as the superconductor is not in the so-called superclean limit (i.e. if the inverse electron-impurities scattering time τ^{-1} is larger than the level separation ω_0). The underlying idea of this theory is that interaction between electrons localized near the (moving) vortex and impurities can be treated as a kind of scattering problem in the continuous spectrum, i.e. similar to the impurity scattering in a normal state.

In the present Letter we will show that in the case of strongly anisotropic (layered) superconductors the validity of the above picture is limited to the situations when inelastic width Γ of the core electronic levels is comparable to or large than the level spacing ω_0 . Note that $\Gamma = \Gamma_{int} + \Gamma_v$, where Γ_{int} is due to electron-electron and (mainly) electron-phonon interactions and grows with temperature, whereas Γ_v is due to nonstationarity of the impurity potential around moving vortex, and grows with its velocity v_v ; therefore the condition $\Gamma \gg \omega_0$ is fulfilled at sufficiently large T or v_v . In the opposite limit,

$\Gamma \ll \omega_0$, the core levels are essentially discrete; as a result, all dissipation induced by the motion of a vortex is due to rare nonadiabatic (Zener) processes of electron excitations between the core levels and subsequent downward electron transitions with emission of phonons. As a result, the longitudinal flux-flow conductivity σ_{xx} becomes reduced compared to its “quasiclassical” value (1), and dependent on the electric field:

$$\sigma_{xx} \leq \frac{ecn_e}{B} \omega_0 \tau \left(1 - \sqrt{\frac{E_*}{E}} \right); \quad E_* \approx \frac{\omega_0^2 B}{c} \sqrt{\frac{\hbar}{\rho s^3}}, \quad (2)$$

where the characteristic electric field E_* is very small, so in the domain of applicability of our theory $E \gg E_*$ (here ρ is the mass density of the crystal, s is some average sound velocity and c is the velocity of light). Note that according to Eq. (2) conductivity *grows* with the increase of electric field (or current), which is the trend opposite to the one known near the classical vortex depinning transition [9]. Our result (2) is expected to be valid in the range of not very high current densities $j \leq j_K = j_0 (k_F l)^{-1/2}$, where $l = v_F \tau$ is the elastic mean-free-path, and $j_0 \sim en_e \Delta / p_F$ is the depairing current density. Note that the above result refers to the moderately clean case $\omega_0 \ll \tau^{-1} \ll \Delta/\hbar$, where the *average* density of states within the core $\langle \nu_c(E) \rangle$ is constant (at $E \geq \hbar\omega_0$) as in normal metal. Therefore the effects we are discussing are of *mesoscopic nature* in the sense that they “feel” the structure of correlations of energy levels. Thus the range of existence of these effects disappears with the growth of $k_F l$: $j_K \propto (k_F l)^{-1/2}$.

We are going to consider strongly anisotropic superconductors with a high effective mass anisotropy $m_c/m_a \gg 1$; it means very weak dispersion of the core level's energies as a function of k_z , $(E_\mu(k_z) - E_\mu(0))/\hbar \sim \mu \omega_0 \frac{m_a}{m_c} \frac{k_z^2}{k_F^2} \ll \omega_0$. It allows, as long as the low-lying levels with $\mu \ll m_c/m_a$ are relevant, to treat the core levels as purely discrete, which formally corresponds to a “pancake” vortex in 2D superconductor (one important point of our arguments where 3D nature of vortex is essential will be explained later).

At low temperatures any dissipation of energy related to the vortex motion is due to transitions between discrete electron states within the core. In the absence of electron-phonon interaction these levels have almost zero width (inelastic width due to electron-electron interactions for the system of discrete levels at low temperatures is even much weaker than the electron-phonon one, cf. [10]), whereas their exact locations depend on the particular realization of impurities in the region of the size $\sim \xi$ around the vortex center $\mathbf{r}_v$. The most direct way to study the statistics of random energy levels is to employ powerful machinery of the Supersymmetric Sigma-Model [11]. Here, however, we prefer to use technically simpler (although less general) path, sufficient for the calculation of dissipation rate in the case $\omega_0\tau \ll 1$. This condition ensures that the position of each level E_i is strongly modified with respect to the bare levels [3] of an ideally clean superconductor. The second important point is that the wavefunctions corresponding to all these levels are confined in the same area $\sim \xi^2$ within the vortex core. Therefore it is quite natural to describe the distribution of levels in terms of an appropriate Random Matrix Ensemble (RME) [12]. When vortex is moving, the realization of disorder in the core region is changing, so the core levels are moving up and down, presenting a new example of a “parametric level statistics” studied before with regard to disordered metallic grains and quantum dots (see e.g. [13]). In our case the parameter $X(t)$ governing the evolution of levels is just the vortex coordinate, so one can try to make use of the relation [15,16,13] between the rate of energy dissipation per pancake vortex (within the applicability of the standard Kubo approach) and the mean-squared level “velocities” $\langle (dE_i/dX)^2 \rangle$:

$$(\partial W/\partial t)_{Kubo} = \frac{\beta}{2} \pi \hbar C(0) (\partial X/\partial t)^2, \quad (3)$$

where $\beta = 1, 2, 4$ for the system described by, respectively, orthogonal, unitary and symplectic Wigner-Dyson ensembles, and $C(0)$ is the normalized dispersion of level “velocities”, $C(0) = \langle (dE_i/dX)^2 \rangle / (\hbar\omega_0)^2$ (here $\hbar\omega_0 = \langle E_{i+1} - E_i \rangle$). Vortex solution breaks T-invariance, whereas leaves intact invariance with respect to spin rotations (here and below we neglect Zeeman spin splitting, which is weak as long as $B \ll H_{c2}$). Therefore one could, at first sight, conclude that the relevant for our problem Wigner-Dyson ensemble is just the Unitary (U) one, with $\beta = 2$. In fact, the situation is a bit more complicated, because of the specific symmetry of the Bogolyubov-De Gennes equations determining the core levels: each of the positive-energy levels $E_i^+ = E > 0$ has its exact mirror counterpart $E_i^- = -E$. As a result, the RME relevant for our problem does not coincide exactly with Unitary or any other of the standard Wigner-Dyson ensembles. Fortunately, the general classification of RME related to the mixed superconductive-normal systems was developed very recently by Atland and Zirnbauer (AZ) [17],

who identified 4 different types of RME depending on the presence or absence of time- and spin-reversal symmetries. The class C of the AZ classification just corresponds to our problem at hand. The level statistics within the C class can be described via the multi-particle “wavefunction” of auxiliary “free fermions” in the same way as it was done for the standard Unitary ensemble [14]; the only difference is the condition of vanishing amplitude of a single-particle “wavefunctions” in the origin of the energy axis $E = 0$. As a result, the level statistics within the C class coincides with that of the U class as far as highly excited states with $E_i \gg \hbar\omega_0$ are involved, but differs for low-lying states.

It is very instructive to compare the dissipation rate obtained via (3) with the results of the quasiclassical kinetic equation approach [4]. As it will become clear soon, the applicability of the result (3) to the vortex dynamics is limited to the case when highly excited levels are important, so at this stage we can neglect difference between C and U ensembles, and use (3) with $\beta = 2$. Comparing the definition of the vortex damping coefficient η ($\partial W/\partial t = \eta \mathbf{v}_v^2$) with Eq. (3), one finds

$$\pi \hbar C(0) = \eta K_{ubo} = \pi \hbar n_{2D} (\omega_0 \tau), \quad (4)$$

where the second equality in (4) follows from the results of [4] in the limit $\omega_0\tau \ll 1$, $n_{2D} = n_e d$ is the areal density of electrons, d is the interlayer spacing, and we put subscript “Kubo” to emphasize that the expression (4) has the same meaning and the domain of applicability as the Kubo-Greenwood formula. The damping coefficient η is proportional to the longitudinal flux-flow conductivity: $\sigma_{xx} = \eta e c / \pi \hbar B$. The parameter $C(0)$ has the dimension of inverse area; one can define characteristic length $\mathcal{L} = C^{-1/2}(0)$ with the following meaning: when vortex moves over the length $\mathcal{L}$, the characteristic displacements of the core levels inside it become of the order of the mean spacing ω_0 . Then Eq. (4) tells us that $\mathcal{L} = (n_{2D} \omega_0 \tau)^{-1/2}$. Note that $\mathcal{L}$ decreases (i.e. sensitivity of the level positions to the shift of a vortex increases) with the decrease of disorder, and becomes of the order of the Fermi wavelength at $\omega_0\tau \sim 1$, i.e. on the border of applicability of Eq. (4). On the other hand, in the extremely disordered limit, $k_F l \sim 1$, the length $\mathcal{L}$ would become of the order of the “clean” coherence length ξ_0 .

There are two ways to understand the relation (3): i) to consider open system with finite width of energy levels and use the standard Kubo-Greenwood approach [13], and ii) to work with strictly discrete levels but take into account the nonadiabatic transitions between time-dependent (due to variation of external parameter X) levels $E_i(X)$, as it was done in [15,16]. The first approach is clearly invalid in our case as far as the inelastic width $\Gamma \ll \omega_0$. Following the second approach [16] we find that Kubo-like expression (4) can be safely used if the characteristic frequency of level perturbations $v_v/\mathcal{L}$

is much higher than ω_0 , i.e. at $v_v \gg v_K = v_0(k_F l)^{-1/2}$, where $v_0 = \Delta/p_F$. On the other hand, at low vortex velocities $v_v \ll v_K$ and low temperatures the probability of Zener transitions between levels is exponentially low ($\sim \exp(-v_K/v_v)$) when the interlevel spacing is of the order of its average value $\hbar\omega_0$. In this case dissipation occurs when in course of “level dynamics” the spacing between some pair of levels becomes very small, $\delta E \leq E_Z = \hbar\omega_0(v_v/v_K)$ and Zener tunneling becomes probable.

The crucial stage of the dissipation process is determined by the non-adiabatic transitions of some electron from the highest negative-energy (filled) core level E_{-1} to the lowest positive-energy level E_0 . The rate of these transitions can be calculated by the method [15] modified for the C class of the AZ classification (details will be published elsewhere [18]):

$$R_0 = v_v \int_0^\infty dA \int_0^\infty d\epsilon N(\epsilon, A) \exp\left(-\frac{2\pi\epsilon^2}{\hbar A v_v}\right) = \frac{\eta_{Kubo}}{2\hbar\omega_0} v_v^2, \quad (5)$$

where $N(\epsilon, A) = \frac{2\pi^{3/2}\epsilon}{3\hbar^2\omega_0^3} \left[\frac{A^2}{8\hbar^2\omega_0^2 C(0)}\right]^{3/2} \exp\left(-\frac{A^2}{8\hbar^2\omega_0^2 C(0)}\right)$ is the joint probability distribution for the energy ϵ of the lowest positive level and its “velocity” A far from the “avoided crossing” region. Note that the rate R_0 is just the factor 2 lower than the analogous result for the Unitary ensemble [15], which would also be valid in our problem if the transitions between highly excited levels would be considered: $R_{|i| \gg 1} \approx 2R_0$. In a similar problem treated in [15] (where all transition rates were equal, $R_i = R$), the rate of energy absorption from the source was given by $\hbar\omega_0 R$, which coincided exactly with the result for the Kubo regime, Eq. (3). This striking coincidence takes place, as was shown in [15,16], *only* for the Unitary ensemble (ensembles with the level repulsion parameter $\beta = 1, 4$ lead to velocity-dependent friction coefficient $\eta \propto v^{\beta/2-1}$).

In our case the situation is more complicated due to i -dependence of the transition rates R_i ; as a result, the dissipation rate depends on the distribution function $f_i(t)$ for the electron’s population of the i ’th core level, which is determined by competition between Zener processes of excitation (the energy being absorbed from the source) and energy relaxation to the phonon “bath” caused by electron-phonon interaction. The rate of electron transitions between the core levels with energy difference $\hbar\omega$ due to emission of 3D phonons can be estimated [18] as $\Gamma(\omega) = \omega\gamma_{ph}$, where $\gamma_{ph} = \nu(\omega_0\tau)\hbar\omega_0^2 n_{2D}/\rho s^3 \ll 1$ (here it is assumed that $T \leq \hbar\omega$, and ν is the numerical coefficient of order 1). Thus the kinetic equation for the distribution function $f_i(t)$ is:

$$\frac{\partial f_i(t)}{\partial t} + R_{i+1}(f_i - f_{i+1}) + R_i(f_i - f_{i-1}) =$$

$$-\omega_0\gamma_{ph} \left(\sum_{j<i} (i-j)f_i[1-f_j] - \sum_{j>i} (j-i)f_j[1-f_i] \right), \quad (6)$$

which is a kind of discrete “diffusion equation” in the energy space. Dimensional estimates show that the characteristic width of the stationary solution f_i^{st} is $i_{char} \sim (R_0/\omega_0\gamma_{ph})^{1/4} \sim \sqrt{v_v/v_K}(\Omega_D E_F/\hbar\omega_0^3\tau)^{1/4}$; usually i_{char} is large since v_v should be larger than the pinning-determined critical velocity v_c , (estimate for v_c/v_K will be given below), whereas the second factor in the above estimate is always very large. One can qualitatively associate with i_{char} some “effective local temperature” $T_{eff}(v_v) \sim \hbar\omega_0 i_{char} \gg \hbar\omega_0$ of the core-localized electrons. Due to large effective width of f_i^{st} , the energy dissipation rate $\partial W/\partial t$ is close to its value $2R_0\hbar\omega_0$ for the Unitary ensemble (all $R_i = 2R_0$), which is also the result in the Kubo regime, as mentioned above. In order to find correction $\eta - \eta_{Kubo}$ we need to specify the rates R_i . It is very difficult to determine R_i for general $i \sim 1$ because of the: i) randomness of energies where “avoided crossing” between levels $i-1$ and i happens and ii) energy-dependence of the mean density of states for the C-ensemble. Thus we employ the simplest model with correct asymptotic behavior of rates: $R_{i \neq 0} = R_\infty = 2R_0$. Within this model and at $i_{char} \gg 1$ we get $\partial W/\partial t = 2R_0(\hbar\omega_0 + \langle E_0 \rangle (f_0 - f_{-1}))$, which leads finally to the upper bound (cf. below) for the vortex damping coefficient $\eta = (\partial W/\partial t)/v_v^2$:

$$\frac{\eta}{\eta_{Kubo}} \leq 1 - \nu_1 \sqrt{\frac{v_K}{v_v}} \cdot \gamma_{ph}^{-1/4}, \quad (7)$$

where $\nu_1 \sim 1$. Eq. (7) together with the relation between vortex velocity and electric field, $v_v = cE/B$, leads to the announced in Eq. (2) result for the conductivity σ_{xx} . Eq. (7) is valid up to temperatures $T \leq T_{eff}(v_v)$; at higher T the width of f_i^{st} and damping coefficient are determined by temperature instead of vortex velocity. Although the final result for σ_{xx} is rather close to the one obtained within quasiclassical picture (where continuous spectrum of electron states is assumed), the intrinsic mechanism of dissipation is quite different. One can understand it in the following terms: the energy dissipation rate is a product of the rate of inelastic transitions R_{in} by the characteristic amount of energy δE transferred at each transition; within our picture R_{in} is much lower than in the quasiclassic approach, whereas δE is much larger by almost the same factor. This consideration suggests that Eq. (2) does not necessarily mean that the resistivity $\rho_{xx} = \sigma_{xx}^{-1}$ as the quasiclassical results (1) would tell us. The point is that Hall conductivity σ_{xy} , being nondissipative, does not vanish in the absence of nonadiabatic transitions and the Hall angle $\theta_H = \arctan(\sigma_{xy}/\sigma_{xx})$ is not necessarily small even at $\omega_0\tau \ll 1$. The calculation of σ_{xy} within our picture will be postponed for the future studies; here we just note that it can’t be done within purely RMT approach, since

the latter neglects completely the correlations between energies of the core levels and their angular momenta. Such correlations (which survive under moderate disorder) are irrelevant for the energy dissipation rate (which depends on the short-scale structure of level correlations only), but are crucial for the transverse nondissipative force acting on a vortex.

We treat Eq. (7) as an upper bound for the dissipation due to the following two reasons: i) we have used, when deriving Eq. (7), a model that overestimates transition rates $R_{n \neq 0}$; ii) we have employed purely classical master equation (6) for the probability distribution function $f_i(t)$. It means that we neglected possible phase coherence of electron states on a time scale R_0^{-1} between two successive Zener transitions. It was shown in [19] that in the opposite case of a strict phase coherence the system exhibits a kind of 1-dimensional localization (with the energy E_n playing the role of a “coordinate”); as a result, $(\partial W/\partial t)_{st} = 0$. We expect these phase-coherence effects to be weak in the case of a 3D vortex composed from “pancakes”, since the multiplicity of allowed electron states corresponding to each “level” (in fact, very narrow band) i means that the problem of energy-localization should be considered as *quasi*-1D, with a rather large number of “transverse channels”. Thus the corresponding “localization length” in the energy space l_E is expected to be large compared to the characteristic width i_{char} of “classical” stationary distribution function, so the energy-localization effects are rather weak. However, these effects should be important for the case of a purely 2D superconductive system.

In the above calculations we have assumed that the vortex is moving with a constant velocity v_v , which means that the driving current density $j = v_v e \eta / (\pi \hbar \cos \theta_H)$ is higher than the pinning-induced critical current density j_c , so the corresponding “critical velocity” $v_c \ll v_v$. On the other hand, v_v was assumed be small compared to $v_K = \Delta / \hbar k_F^{3/2} l^{1/2}$. Critical current density for the pinning of individual pancake vortex in layered superconductor on weak impurities can be estimated [9] as $j_c \approx j_0 (0.1 \sigma_{imp} / l d)^{1/2}$, where j_0 is the depairing current density and $\sigma_{imp} = (l n_i)^{-1}$ is the electron-impurity scattering crosssection (n_i is the impurity concentration). Using “pessimistic” estimate $\theta_H \ll 1$ we get the compatibility condition for our theory in the form $5 \cdot 10^{-2} k_F \sigma_{imp} / d \ll (\omega_0 \tau)^2 \leq 1$. Thus the proposed scenario may be realized in the case of very weak impurities with a crosssection small on atomic scale. Note however that the above condition may actually be less stringent due to the decrease of j_c with the magnetic field already in the range $B \ll H_{c2}$ [9], and also in the presence of a considerable Hall component of motion, $\tan \theta_H \geq 1$. We believe that the necessary conditions may be fulfilled in the clean single crystals of layered superconductor NbSe₂ where the main source of disorder is due to random substitution of small percentage of Nb

by Ta, which is known to produce very weak impurity centers [20]. Our results may also be relevant for layered HTSC, however in that case the role of *d*-wave pairing symmetry should be studied.

In conclusions, we proposed new mechanism of flux-flow dissipation operative in layered superconductors at low temperatures. Dissipative conductivity σ_{xx} is found to be close to the classical results [1,4] but is slowly field-dependent. We suggest that, under the same conditions, the Hall conductivity σ_{xy} and the flux-flow resistivity ρ_{xx} may differ considerably from their classical values. Useful discussions with B.L.Altshuler, S.Bhattacharya, V.B.Geshkenbein, N.B.Kopnin, V.E.Kravtsov, A.I.Larkin, V.M.Marikhin, V.P.Mineev and G.E.Volovik are gratefully acknowledged. This research was supported by the RFBR grant # 95-02-05720, DGA grant # 94-1189 (M.V.F.) and ISSEP grant # a96-568 (M.A.S.).

-
- [1] J. Bardeen and M. Steven, Phys.Rev. **140**, A1197 (1965).
 - [2] P. Nozieres and W. F. Vinen, Phil.Mag. **14**, 667 (1967).
 - [3] C. Caroli, P. G. De Gennes and J. Matricon, Phys.Lett. **9**, 307 (1964).
 - [4] V. E. Kravtsov and N. B. Kopnin, Pis'ma Zh.E.T.F. **23**, 631 (1976) [JETP Lett. **23**, 578 (1976)] and Zh.E.T.F. **71**, 1644 (1976) [JETP **44**, 861 (1976)]; N. B. Kopnin and M. M. Salomaa, Phys. Rev. B **44**, 9667 (1991).
 - [5] N. B. Kopnin and A. V. Lopatin, Phys.Rev. **B51**, 15291 (1995); N. B. Kopnin, G. E. Volovik and Ü. Parts, Europhys. Lett. **32**, 651 (1995).
 - [6] M. V. Feigel'man, V. G. Geshkenbein, A. I. Larkin and V. M. Vinokur, Pis'ma Zh.E.T.F. **62**, 811 (1995) [JETP Letters **62**, 834 (1995)].
 - [7] A. van Otterlo *et al*, Phys.Rev.Lett. **75**, 3736 (1995).
 - [8] A. I. Larkin and Yu. N. Ovchinnikov, Zh.E.T.F. **73**, 299 (1977) [JETP **41**, 960 (1977)].
 - [9] G. Blatter *et al*, Rev.Mod.Phys. **66**, 1125 (1994).
 - [10] Ya. Blanter, cond-mat/9604101; B. L. Altshuler *et al*, cond-mat/9609132.
 - [11] K. B. Efetov, Adv.Phys. **32**, 53 (1983).
 - [12] M. L. Mehta, *Random Matrices*, Acad. Press, 1991.
 - [13] B. D. Simons and B. L. Altshuler, Phys. Rev. **B 48**, 5422 (1993).
 - [14] B. D. Simons, P. A. Lee and B. L. Altshuler, Nucl.Phys. **B409**, 487 (1993).
 - [15] M. Wilkinson, J.Phys. A: Math.Gen. **21**, 4021 (1988).
 - [16] M. Wilkinson, Phys.Rev. **A 41**, 4645 (1990); M. Wilkinson and E. J. Austin, Phys. Rev. **A 46**, 64 (1992).
 - [17] A. Atland and M. R. Zirnbauer, cond-mat/9602137.
 - [18] M. A. Skvortsov and M. V. Feigel'man, in preparation.
 - [19] G.Blatter and D.A.Browne, Phys.Rev.**B37**, 3856 (1988); Yu. Gefen and D. J. Thouless, Phys.Rev.Lett. **59**, 1752 (1987) and Phil. Mag. **B 56**, 1005 (1987); E. Shimshoni and Yu. Gefen, Ann. Phys. **210**, 16 (1991).
 - [20] S. Bhattacharya, Physica **C 257**, 232 (1996).